

# (12) UK Patent Application (19) GB (11) 2 161 110 A

(43) Application published 8 Jan 1986

(21) Application No 8513604

(22) Date of filing 30 May 1985

(30) Priority data

(31) 8417419

(32) 7 Jul 1984

(33) GB

(71) Applicant

Rolls-Royce Limited (United Kingdom),  
65 Buckingham Gate, London SW1E 6AT

(72) Inventor

James Pears Angus

(74) Agent and/or Address for Service

M A Gunn,  
Patents Department, Rolls-Royce Limited, PO Box 31,  
Moor Lane, Derby DE2 8BJ

(51) INT CL<sup>4</sup>

B29C 45/14 F01D 5/00 5/22 5/28 // B29K  
73:00 105:14 105:20 B29L 31:08

(52) Domestic classification

B5A 1R214E 1R214F 1R314C1S 1R314C2S 1R447  
20T14 B11 B2  
F1V 106 111 406 410 412 CW  
U1S 2036 B5A F1V

(56) Documents cited

None

(58) Field of search

B5A  
B3F  
F1V

(54) An annular bladed member having an integral shroud and a method of manufacture thereof

(57) A gas turbine engine disc (22) having integral, radially extending aerofoil blades (23) and an integral shroud (30) interconnecting the radially outer extents of the blades is described. In the manufacture thereof continuous fibres (16) are wound around an annular array of inserts provided in a mould. The inserts define the spaces between adjacent blades on the disc. A mixture of short fibres, eg chopped carbon fibre, and a matrix material, eg an epoxy resin, is then injected into the central portion of the mould such that the short fibres (24) within the blade portions are radially aligned. Any wound fibres which have not been impregnated are subsequently impregnated by a matrix material. Alternatively a preformed ring-shaped shroud member may be used and the fibre/matrix material is then injected to abut the shroud.

Fig. 6.





Fig. 7.



BEST AVAILABLE COPY

GB 2 161 110 A

Fig. 1.




Fig. 2.




Fig. 3.




Fig. 4.




Fig. 5.







Fig. 6.



*Fig. 7.*



*Fig. 8.*



## SPECIFICATION

**An annular bladed member having an integral shroud and a method of manufacture thereof**

This invention relates to an annular bladed member having an integral shroud and in particular to an annular bladed member having an integral shroud which bladed member is formed from a fibre reinforced composite material. The invention also relates to a method of manufacturing such a bladed member.

It is known to manufacture discs with integral aerofoil blades, for instance those which are suitable for use in an axial flow compressor of a gas turbine engine, by injecting an appropriate resin matrix material into a die which contains reinforcing fibres which have been aligned in a predetermined manner. There are problems with such a method of manufacture however in ensuring that the fibres remain in the desired configuration during the injection moulding operation. Moreover it is difficult to ensure that all of the fibres are so disposed as to provide a bladed disc with optimum strength characteristics. A further disadvantage of the method is that it can be expensive in view of the fact that the reinforcing fibres usually have to be laid up by hand.

It is an object of the present invention to provide an annular bladed member formed from a fibre reinforced composite material which is cheap to manufacture and has good strength characteristics. It is an additional object of the present invention to provide a method of manufacturing such an annular member.

According to the present invention, an annular bladed member comprises a disc having a plurality of integral radially extending aerofoil blades on the periphery thereof and a central aperture and an integral shroud interconnecting the radially outer extents of said blades, said disc and aerofoil blades being formed from a composite material comprising a plurality of short reinforcing fibres dispersed within a matrix material, at least the majority of said short reinforcing fibres within said aerofoil blades being generally radially aligned, said shroud being formed from substantially continuous circumferentially extending reinforcing fibre enclosed in a matrix material.

According to a further aspect of the present invention, a method of manufacturing an annular bladed member comprising a disc having a plurality of radially extending aerofoil blades on the periphery thereof and a central aperture and an integral shroud interconnecting the radially outer extents of said blades from a fibre reinforced composite material comprises locating a ring-shaped shroud

member comprising substantially continuous circumferentially extending reinforcing fibre enclosed in a matrix material around the radially outer extents of an annular array of inserts provided in a dividable die defining the form of said integral bladed member, said inserts being so configured as to define the spaces between adjacent aerofoil blades, closing said die and injecting a mixture of short fibres dispersed in a matrix material into the central portion of said die interior so that said mixture fills said central portion and flows between said inserts to reach and abut said ring shaped shroud member so that the majority of said short fibres, between said inserts, are generally radially aligned.

According to a further aspect of the present invention, a method of manufacturing an annular bladed member comprising a disc having a plurality of integral radially extending aerofoil blades on the periphery thereof and a central aperture and an integral shroud interconnecting the radially outer extents of said blades from a fibre reinforced composite material comprises winding a substantially continuous fibre around the radially outer extents of an annular array of inserts provided in a dividable die defining the form of said integral bladed member, said inserts being so configured as to define the spaces between adjacent blades on said disc, so that said fibre constitutes the reinforcing fibre of said shroud, closing said die and injecting a mixture of short fibres dispersed in a matrix material into the central portion of said die interior so that said mixture fills said central portion and flows between said inserts, so that the majority of said short fibres between said inserts are generally radially aligned, to impregnate said wound fibre, injecting a matrix material into said wound fibre so as to impregnate any part thereof which has not been impregnated by said mixture of matrix material and short fibres so as to define said integral shroud and subsequently opening said die to release the thus produced integral bladed member.

The invention will now be described, by way of example, with reference to the accompanying drawings in which

*Figures 1 to 5* illustrates various stages in the method of manufacturing a bladed disc having an integral shroud in accordance with the present invention.

*Figure 6* illustrates a bladed disc in accordance with the present invention.

*Figure 7* is a sectioned view of a portion of the bladed disc shown in *Fig. 6*.

*Figure 8* is a sectioned view of a portion of the bladed disc shown in *Fig. 6* when mounted on a rotary shaft.

With reference to *Figs. 1 to 5*, one part 10 of the dividable die 11 comprises a disc-shaped portion 12 upon which is fixed an annular array of inserts 13. The inserts 13 are

so configured that the adjacent surfaces 14 thereof cooperate to define the flanks of an annular array of radially extending circumferentially spaced apart aerofoil blades. The disc-shaped portion 12 is additionally provided with a cylindrical insert 15 at the centre thereof for the purpose of defining a central hole in the bladed disc which is to be produced.

10 A dry continuous length of carbon fibre 16 is wound under tension around the radially outer extents of the inserts 13 to define a ring of fibre as can be seen in Fig. 2 which will constitute the reinforcement of a continuous shroud on the bladed disc which is to be produced. Such a shroud is necessary in order to resist the centrifugal loads imposed upon the aerofoil blades during rotation. The die 11 is then closed as can be seen in Fig. 3 by the other portion 17 thereof to define an enclosure which defines the form of a bladed disc having a continuous integral shroud. The die 11 has a central access port 18 and a plurality of radially outer access ports 19 around its peripheral surface. A plurality of nuts and bolts 20 serve to hold the die parts 10 and 17 together.

The die 11 is then placed in a conventional injection moulding machine 21 as shown in Fig. 4 and a mixture of short chopped carbon fibres and an epoxy resin is injected into the die 11 through its central access port 18. The fibre/resin mixture fills the central cavity within the die 11 to define a disc 22 as can be seen in Fig. 6, and then flows between the adjacent surfaces 14 of the inserts 13 to define a plurality of radially extending aerofoil blades 23 (also shown in Fig. 6) which are integral with the disc 22. Fig. 7 indicates the flow pattern of the fibre/resin mixture after it has flowed between the inserts 13. It will be seen that the constriction to flow provided by the inserts 13 causes the individual chopped fibres 24 between the inserts 13 to align in a radial direction. Moreover the chopped fibres 24 in the regions of the radially inner parts of the aerofoil blades 23, although not radially extending, are so disposed as to promote a strong bond between the aerofoil blades 23 and the disc 22. It will also be seen from Fig. 7 that some of the injected fibre/resin mixture flows into the wound carbon fibre 16 surrounding the inserts 13. This causes a certain degree of impregnation of the wound carbon fibre 16 so that there is mechanical interlinking of the chopped fibres 24 with the wound fibre 16. It will be seen therefore that this interaction of chopped and wound fibre results in a strong bond between the thus formed aerofoil blades 23 and the wound fibre 16.

Completion of the impregnation of the wound carbon fibre 16 is achieved by injecting an epoxy resin through delivery tubes 24 inserted into the access ports 19 in the die

portion 17, thereby defining the continuous integral shroud 30 which interconnects the radially outer extents of the aerofoil blades 23.

70 As soon as complete impregnation of the wound carbon fibre 16 has been achieved, the die 11 is placed in an oven and subjected to an appropriate heating cycle in order to cure the resin. The die 11 is then removed from the oven and allowed to cool before being divided to provide access to the thus produced bladed disc 25 which can be seen in Fig. 6.

As stated earlier the cylindrical insert 15 serves to define a central hole in the bladed disc 25 and this can be seen in Fig. 6 as the hole 26. The hole 26 facilitates the mounting of the bladed disc 25 on a rotatable gas turbine engine shaft 27 part of which can be seen in Fig. 8. A flange 28 is provided on the shaft 27 to receive the bladed disc 25. Aligned apertures 29 and 31 respectively are provided in the bladed disc 25 and flange 28 to accept bolts (not shown) which attach the two to each other.

In an alternative method of manufacture in accordance with the present invention, the above described method is repeated with the exception that the wound fibre 16 is replaced by a ready formed ring-shaped shroud member and the shroud injection step is omitted. Such a shroud member would comprise continuous carbon fibre in an epoxy resin matrix material. In such a method of manufacture however, the injected fibre/resin mixture would not of course impregnate the shroud. The epoxy resin in the shroud could be cured prior to injection moulding or alternatively could be uncured so that it is subsequently cured along with the epoxy resin in the injected fibre/resin mixture.

Although the present invention has been described with reference to the manufacture of a bladed disc 25 which is made from carbon fibre, both chopped and continuous, in an epoxy resin matrix, other suitable materials may be used if so desired. Thus the shroud 30 of the bladed disc 25 could be reinforced by fibres of silicon carbide, steel or alumina and have a matrix material of aluminium or alloys thereof, magnesium or alloys thereof, titanium or alloys thereof or a polyimide resin. Similarly the disc 22 and aerofoil blades could be injection moulded with chopped fibres or silicon carbide or alumina in a matrix of aluminium or alloys thereof or magnesium, or alloys thereof or titanium or alloys thereof or alternatively in a matrix of a high temperature resistant thermoplastic polymer such as polyetheretherketone or a polyethersulphone. Moreover the disc 22 and aerofoil blades 23, and the shroud 30 need not be formed from the same combination of fibre and matrix material.

130 It is envisaged that the method of the

present invention could be used in the manufacture of bladed rotors 25 which are so configured with re-entrant features that they could not be easily removed from the die 11 after moulding. In such circumstances, mould inserts 13 for instance could be used which are made from a low melting point alloy. The alloy would be melted out prior to the removal of the bladed disc 25 from the die 11. If the bladed rotor 25 is made from a fibre reinforced metal matrix material then water dispersible ceramic based inserts 13 could be used instead.

Although the present invention has been described with reference to a bladed rotor and a method of manufacturing such a bladed rotor, it will be appreciated that it is not restricted to rotor members and that it could be applied to stator members. In the case of a stator annular bladed member, the disc supporting the aerofoil blades would have a larger diameter aperture in the centre thereof so that the apertured disc is effectively a ring member providing support for the radially inner portions of the aerofoil blades.

#### CLAIMS

1. An annular bladed member comprising a disc having a plurality of integral radially extending aerofoil blades on the periphery thereof and a central aperture and an integral shroud interconnecting the radially outer extents of said blades, said disc and aerofoil blades being formed from a composite material comprising a plurality of short reinforcing fibres dispersed within a matrix material, at least the majority of said short reinforcing fibres within said aerofoil blades being generally radially aligned, said shroud being formed from substantially continuous circumferentially extending reinforcing fibre enclosed in a matrix material.

2. A method of manufacturing an integral bladed member as claimed in claim 1 comprising winding a substantially continuous fibre around the radially outer extents of an annular array of inserts provided on a dividable die defining the form of said integral bladed member, said inserts being so configured as to define the spaces between adjacent blades on said member, so that said fibre constitutes the reinforcing fibre of said shroud, closing said die and injecting a mixture of short fibres in a matrix material into the central portion of said die interior so that said mixture fills said central portion and flows between said inserts so that the majority of said short fibres between said inserts are generally radially aligned to partially impregnate said wound fibre, injecting a matrix material into said wound fibre so as to impregnate any part thereof which has not been impregnated by said mixture of matrix material and short fibres so as to define said integral shroud, and subsequently opening

said die to release the thus produced integral bladed member.

3. A method of manufacturing an integral bladed member as claimed in claim 2 wherein said substantially continuous fibre wound around the radially outer extents of said inserts is so wound under tension.

4. A method of manufacturing an integral bladed member as claimed in claim 1 comprising locating a ring-shaped shroud member comprising substantially continuous circumferentially extending reinforcing fibre enclosed in a matrix material around the radially outer extents of an annular array of inserts provided in a dividable die defining the form of an integral bladed member, said inserts being so configured as to define the spaces between adjacent aerofoil blades, closing said die and injecting a mixture of short fibres dispersed in a matrix material into the central portion of said die interior so that said mixture fills said central portion and flows between said inserts to reach and abut said ring shaped shroud member so that said short fibres, at least between said inserts, are generally radially aligned.

5. A method of manufacturing an integral bladed member as claimed in any one of claims 2, 3 and 4 wherein said substantially continuous fibre in said integral shroud is carbon, silicon carbide, steel or alumina.

6. A method of manufacturing an integral bladed member as claimed in any one of claims 2 to 5 wherein said short fibres are of carbon, silicon carbide or alumina.

7. A method of manufacturing an integral bladed member as claimed in any one of claims 2 to 6 wherein said matrix material mixed with said short fibres is an epoxy resin, a polyetheretherketone resin, a polyethersulphone resin, aluminium or an alloy thereof, or magnesium or an alloy thereof, or titanium or an alloy thereof.

8. A method of manufacturing an integral bladed member as claimed in one of claims 2 to 7 wherein said matrix material in said integral shroud is an epoxy resin, a polyimide, aluminium or an alloy thereof.

9. A method of manufacturing an integral bladed member as claimed in any one of claims 2 to 8 wherein said inserts are formed from a low melting point alloy, said alloy being melted prior to the removal of said thus produced bladed member from said die.

10. A method of producing an integral bladed member as claimed in any one of claims 2 to 8 wherein said inserts are formed from water dispersible ceramic based composition.

11. A method of manufacturing an annular bladed member having integral radially extending aerofoil blades and an integral shroud interconnecting the radially outer extents of said blades substantially as hereinbefore described with reference to the accom-

panying drawings.

12. An integral bladed member substantially as hereinbefore described with reference to the accompanying drawings.

---

Printed in the United Kingdom for  
Her Majesty's Stationery Office, Dd 8818935, 1986, 4235.  
Published at The Patent Office, 25 Southampton Buildings,  
London, WC2A 1AY, from which copies may be obtained.

BEST AVAILABLE COPY